

建源美耐地板

試驗報告



報告編號： TB-14-03403Z
C-14-13267

頁數： 1 OF 1
報告日期： 103年07月29日


工程名稱： 自測
 承包商： ----
 委託單位： 建源建材股份有限公司
 供料廠商： ----
 樣品名稱： 超耐磨強化複合地板 (9 mm)
 送驗人員： 建源建材股份有限公司-顏文宏
 收件日期： 103年07月03日
 試驗日期： 103年07月03日~103年07月29日
 備註： 1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.本樣品由SGS材料及工程實驗室-高雄（申請書號碼：KV-14-06355W，
 收件日期：103年06月26日）轉送至本實驗室執行本報告所示之試驗項目

=====
 試驗結果：

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	1.4	0.05	CNS 11342(2006)
甲醛釋出量-平均值 (mg/L)	1.4	0.05	

-----000-----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



材料及工程實驗室-高雄

試驗報告



報告編號：KB-14-07033X
C-14-14099

頁數：1 OF 1
報告日期：103年07月14日

委託單位：建源建材股份有限公司
 樣品名稱：超耐磨強化複合地板
 送驗人員：建源建材股份有限公司(顏文宏)
 收件日期：103年05月13日
 試驗日期：103年05月13日~103年06月06日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製


試驗結果：

試驗項目	試驗方法	試驗結果			
		第一片	第二片	第三片	第四片
浸水剝離	CNS 11342(2006)	第六層第三面 未剝離長度<2/3	第十層第三面 未剝離長度<2/3	未剝離長度 >2/3 以上	第六層第四面及 第十層第一面 未剝離長度<2/3

註：本試驗報告引用 KB-14-04797X C-14-09674 之數據。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準


 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB3409047

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

No.61, Kai-Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121 f (886-7) 301-1165

www.sgs.tw

Member of SGS Group

kaoru_liu



材料及工程實驗室-台中

試驗報告



報告編號：TB-14-02493X
C-14-09806

頁數：1 OF 1
報告日期：103年05月26日

工程名稱：自測
 承包商：-----
 委託單位：建源建材股份有限公司
 供料廠商：-----
 樣品名稱：超耐磨強化複合地板
 送驗人員：建源建材股份有限公司-顏文宏
 收件日期：103年05月15日
 試驗日期：103年05月15日~103年05月26日

備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.本樣品由SGS材料及工程實驗室-高雄(申請書號碼：KB-14-04797X C-14-09674，
 收件日期：103年05月13日)轉送至本實驗室執行本報告所示之試驗項目

試驗結果：

試驗項目	試驗結果	CNS 7614(1994) 防焰一級規範值	CNS 7614(1994) 防焰二級規範值	CNS 7614(1994) 防焰三級規範值	試驗方法
火源加熱時間(sec)	30	-----	-----	-----	CNS 7614(1994) A法
餘焰時間(sec)	0.0	≤ 1	≤ 5	≤ 5	
餘燼時間(sec)	0.0	≤ 60	≤ 60	≤ 60	
炭化長度(cm)	3.6	≤ 5	≤ 10	≤ 15	

註：1.樣品平均厚度 8.8 mm
 2.試驗者：周上筆
 3.樣品厚度大於CNS 7614(1994)所規定之允許最大厚度，故無法出具TAF標誌之報告

-----oOo-----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB 3432654

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

No. 9, 14th Rd. Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市台中工業區14路9號
☎ (886-4) 2359-1515

☎ (886-4) 2359-2557

www.sgs.tw

Member of SGS Group

ceddy_yang



材料及工程實驗室-台中

試驗報告



報告編號：TB-14-03404X

C-14-13268

頁數：1 OF 1

報告日期：103年07月16日

工程名稱：自測
 承包商：-----
 委託單位：建源建材股份有限公司
 供料廠商：-----
 樣品名稱：超耐磨強化複合地板
 送驗人員：建源建材股份有限公司-顏文宏
 收件日期：103年07月03日
 試驗日期：103年07月03日~103年07月16日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.本樣品由SGS材料及工程實驗室-高雄(申請書號碼：KV-14-06355，
 收件日期：103年06月26日)轉送至本實驗室執行本報告所示之試驗項目

試驗結果：

試驗項目	試驗結果	試驗方法
耐磨性-10000轉	底材未露出	ASTM D4060-10

註：耐磨試驗之片數為1片，磨耗輪為CS-10，附加於試片之載重為250公克，
 磨耗試驗機的旋轉盤的旋轉速度為60 r/min。

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic formal documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB3434106

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

No. 9, 14th Rd. Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市台中工業區14路9號
t (886-4) 2359-1515 f (886-4) 2359-2557 www.sgs.tw

Member of SGS Group

dofe_ou